

vydyne 20NSP Series data sheet

20NSP Natural, 20NSP Black nucleated, general-purpose nylon

Product Description

Vydyne® 20NSP is a general-purpose, highly nucleated Nylon 66 resin with internal and external lubricant. Available in natural and black.

It is designed to crystallize rapidly when cooled from the molten state. This rapid crystallization can result in reduced cycle times and increased productivity through faster part setup when compared with standard general purpose Nylon 66 resins. The crystalline structure resulting from nucleation will alter part properties, yielding increased modulus or rigidity, increased tensile strength, reduced elongation, reduced impact strength, and mold shrinkage compared with standard general-purpose Nylon 66.

Vydyne 20NSP Series resins have an internal lubricant for improved machine feed and mold release. This formulation is designed to provide easy release of parts from molds using standard molding conditions. The rapid crystallization of Vydyne 20NSP resins may allow part ejection at higher temperatures compared with general-purpose Nylon 66. This will reduce the mold closed time and thereby decrease the molding cycle. Critical factors unique to each application such as mold/part design, tolerances, etc., may negate these cycle time benefits. It is recommended to check critical part dimensions against specifications before implementing shorter molding cycles on a routine basis.

Typical Applications/End Uses

Typical end uses for Vydyne 20NSP are terminal blocks, bearings, business control cams, electrical connectors, housings, wire ties, fasteners, switch components, and general industrial parts that require stiffness and rigidity.



Vydyne 20NSP Specifications and Regulations

ASTM

Conforms to ASTM D-4066 PA0131

Conforms to ASTM D-6779 PA0131

Federal*

Conforms to Federal Specification LP-410a

Military*

Conforms to Military Specification

* Superseded by ASTM D-4066

Find more information or contact us at www.vydyne.com



Typical Properties for Vydyne 20NSP Series

Test temperature 23°C unless otherwise noted

Physical Properties	Test Conditions	Dry as Molded	Conditioned 2.5% Moisture
Specific Gravity (g/cm ³)	ISO 1183	1.14	—
Mold Shrinkage (%)	ISO 294-4		
2 mm - Parallel		0.8	—
2 mm - Normal		1.2	—
Water Absorption @ 23°C (%)	ISO 62		
24 Hours		1.1	—
Equilibrium at 50% RH		2.4	—
Mechanical Properties	Test Conditions	Dry as Molded	Conditioned 2.5% Moisture
Tensile Strength @ Yield (MPa)	ISO 527	98	72
Tensile Strength @ Break (MPa)	ISO 527	—	—
Elongation @ Yield (%)	ISO 527	4.5	25
Elongation @ Break (%)	ISO 527	13	55
Tensile Modulus (MPa)	ISO 527	3,600	1,750
Poisson's Ratio	ISO 527	0.41	—
Flexural Modulus (MPa)	ISO 178	3,500	1,900
Flexural Strength (MPa)	ISO 178	95	24
Notched Charpy Impact (KJ/M ²)	ISO 179		
23°C		4.7	—
-30°C		4.6	—
Unnotched Charpy Impact (KJ/M ²)	ISO 179		
23°C		NB	—
-30°C		NB	—
Notched Izod Impact (KJ/M ²)	ISO 180	3.3	—
Thermal Properties	Test Conditions	Dry as Molded	Conditioned 2.5% Moisture
Melting Point (°C)	ISO 3146	260	—
Heat Deflection Temperature (°C)	ISO 75		
1.82 MPa		78	—
0.45 MPa		231	—
Vicat @ 50N (°C)	ISO 306	240	—
Coefficient of Linear Thermal Expansion	ISO 11359		
2 mm - Parallel, 23°C-55°C (10 ⁻⁵ mm/mm/°C)		1.2	—
2 mm - Normal, 23°C-55°C (10 ⁻⁵ mm/mm/°C)		1.2	—
Electrical Properties	Test Conditions	Dry as Molded	Conditioned 2.5% Moisture
Dielectric Strength (kV/mm) (step-by-step) 3.0 mm	IEC 60243	12	—
Volume Resistivity (ohm-cm x 10 ¹⁵) 3.0 mm	IEC 60093	6	—
Comparative Tracking Index (volts) 3.0 mm	IEC 60112	> 600	—

Flammability Properties for Vydyne 20NSP

Flammability Properties	Test Conditions	Dry as Molded
Glow Wire Flammability Index (GWFI/°C)	IEC 60695-2-12	
0.71 mm		800
1.5 mm		800
3.0 mm		930
Glow Wire Ignition Temperature (GWIT/°C)	IEC 60695-2-12	
0.71 mm		700
1.5 mm		700
3.0 mm		700
Limiting Oxygen Index (%)	ASTM D-2863	26

Typical Molding Conditions for Vydyne 20NSP Series

Optimal processing conditions will depend on such features as machine size, screw design, die design, and material residence time. The settings below are a guide to achieving stable processing and good part quality. It is best to use a hand-held pyrometer to measure stock melt temperature in an air shot.

Underwriters Laboratories Recognized Component Ratings

Yellow Card File Number E70062

Color: All

Parameters	Test Conditions	Thickness (mm)			
		0.4	0.71	1.5	3.0
Temperature Index (°C)	UL 746B				
Electrical		130	130	130	130
Mechanical w/Impact		75	75	75	75
Mechanical w/o Impact		75	85	85	85
Hot Wire Ignition (Rating)	UL 746A	—	4	3	2
UL94 Flammability Class (Rating)	UL Flame Test	V-2	V-2	V-2	V-2
High Amperage Arc Ignition (Rating)	UL 746A	—	0	0	0
High Volt Track Rate (Rating)	UL 746A	—	—	—	0
D495 Arc Resistance (Rating)	UL 746A	—	—	—	5
UL 746A Track Rate (CTI) (Rating)	UL 746A	—	—	—	0

Virgin and regrind up to 50% by weight have the same basic material characteristics.

All numerical flame spread ratings appearing in this data sheet are not intended to reflect hazards presented by this or any other material under actual fire conditions. Each end user should determine whether potential fire hazards are associated with the finished product and whether Vydyne resin is suitable for the particular use. Products made from Vydyne resins should not be exposed to open flames. In the case of direct exposure to open fire, Vydyne resins and products made therefrom can ignite and burn. Always store and use finished products in locations well away from open flames and sources of ignition.

Suggested Machine Conditions

Melt Temperature, 275 to 305 °C

Parameters	Machine Settings
Cylinder Settings °C	270 to 310
Mold Surface Temperature, °C	15 to 95
Injection Pressure, MPa	55 to 140
Holding Pressure, MPa	55 to 140
Injection Time, sec	< 1 to 2.5
Screw Back Pressure, MPa	0.2 to 1.0
Screw Speed, rpm	50 to 150
Cushion, mm	3.0 to 6.4
Clamp Pressure, tons/cm ²	0.3 to 0.7

vydyne 20NSP Series data sheet

20NSP Natural, 20NSP Black nucleated, general-purpose nylon

Suggested Guidelines for Molding

1. Your Vydyne nylon resins arrive packaged in moisture-protected containers. If you do not open the original package prior to use, then drying is not necessary. However, if drying is necessary, we recommend that you use a dehumidified air-type dryer (desiccant bed) with a maximum air temperature of 70°C for 1 to 3 hours.
2. The recommended melt temperatures for Vydyne general-purpose resins are 275 to 305°C. Measure the stock in an air shot with a hand-held pyrometer. In addition to the barrel heater bands, screw back pressure and rotation speed add heat to the melt.
3. Maintain mold surface temperatures in a range of 15 to 95°C. We recommend temperatures on the high end, as the molding cycle allows, to aid in mold filling and to improve the appearance of the molded part.
4. Injection fill rates should be fast. Minimize the use of back pressure 0.2 to 1.0 MPa to yield a consistent melt and/or adequate mixing of color concentrates. Set the screw rotation speed at the minimum required to maintain the molding cycle (50 to 150 rpm).
5. Hold pressure should be set high enough to prevent screw bounce. Hold time should be set until the gate freezes.
6. Maintain your machine's shot-weight-to-barrel-size ratio at 40% to 80% of rated (polystyrene) capacity. A lower shot-to-barrel ratio results in excess residence time and polymer degradation, which can permanently embrittle the molded part. At a shot-to-barrel ratio above the recommended ratio, molding machinery is often unable to deliver a uniform melt or the desirable fast mold fill.
7. Regrind must be dry when molded. The preferred procedure is to grind and reuse immediately after molding. Regrind-to-virgin ratios of 25% or less have shown no significant property loss when properly molded. However, to ensure adequate performance of your molded part, determine acceptable levels for each application through actual part testing.



North America

+1-888-927-2363

Europe

+32 (10) 48 10 05

Asia

+86-21-6361-2266

Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "Information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials, LLC makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials, LLC be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information or the products to which Information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment, or formulation in conflict with any patent, and Ascend Performance Materials, LLC makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose, or of any other nature are made hereunder with respect to Information or the product to which Information refers.

www.vydyne.com © 2009 Vydyne is a registered trademark of Ascend Performance Materials, LLC. [27694-sw-09/09] DTS-20NSP-ENG

